

Materials Research Express



PAPER

Tallow amphopolycarboxyglycinate-stabilized silver nanoparticles: new frontiers in development of plant protection products with a broad spectrum of action against phytopathogens

RECEIVED
15 May 2016REVISED
18 June 2016ACCEPTED FOR PUBLICATION
28 June 2016PUBLISHED
21 July 2016Yurii A Krutyakov^{1,2}, Alexey A Kudrinskiy^{1,2}, Pavel M Zherebin^{1,2}, Alexey D Yapryntsev³, Marina A Pobedinskaya¹, Sergey N Elansky¹, Albert N Denisov⁴, Dmitry M Mikhaylov⁵ and Georgii V Lisichkin^{1,2}¹ Lomonosov Moscow State University, Leninskie Gory, building 1-3, Moscow, 119991, Russia² National Research Centre 'Kurchatov Institute', Akademika Kurchatova pl. 1, Moscow, 123182, Russia³ Kurnakov Institute of General and Inorganic Chemistry of the Russian Academy of Sciences, Moscow 119991, Russia⁴ Grand Harvest Research International Ltd, 7 Ronda Doctor Turró, 9-B Mataró, Barcelona, E-08303, Spain⁵ Huazhong University of Science and Technology, 1037 Luoyu Road, Wuhan, People's Republic of ChinaE-mail: yurii@petrol.chem.msu.ru**Keywords:** silver nanoparticles, aggregation kinetics, fungicidal activity, polyampholytes, *Phytophthora infestans*, fungi, DLSSupplementary material for this article is available [online](#)**Abstract**

Sustainable agriculture calls for minimal use of agrochemicals in order to protect the environment. It has caused an increase in the rate of nanoparticles use, in particular silver nanoparticles (AgNPs) due to their safety for mammals, unique biological activity and a broad spectrum of action against fungal and bacterial pathogens. Until now the use of AgNPs dispersions in the agricultural sector has been essentially limited due to many factors decreased their stability (mixing with other pesticides, presence of electrolytes). We present a versatile synthesis of polyampholyte surfactant (tallow amphopolycarboxyglycinate) stabilized AgNPs. We took a close look at unique aggregation behavior (via dynamic light scattering and UV–vis spectroscopy) and biocidal activity of obtained silver colloids. AgNPs are characterized by exclusively high aggregative stability in the presence of coagulating agents NaNO₃ and NaSO₄ (up to 1 M), during drying/redispersion, and frost/thaw cycles. The dispersion of AgNPs shows high biocidal activity (EC₅₀ is ten times lower than commercial species ones) with respect to *Phytophthora infestans* and phytopathogenic fungi. This points to the possibility of successful application of silver preparations within agriculture with the goal of partial reduction of the use of toxic and expensive synthetic antibiotics and pesticides.

1. Introduction

Silver nanoparticles (AgNPs) and their antibacterial and antifungal action are quickly gaining relevance in human medicine, veterinary medicine and agriculture due to being less toxic to people, animals and plants than cations of silver [1]. The explosive growth in the number of pathogenic microorganisms resistant to the action of antibiotics and pesticides also draws attention to AgNPs; as it stands, the resistance to silver de novo is difficult to acquire [2]. Furthermore, silver compounds have immunomodulating effect [3] and stimulate growth and development of plants [4].

Wide use of AgNPs colloids against pathogenic microorganisms is essentially limited by the inclination of silver sols to coagulate during dilution, action of electrolytes and many other factors [5]. For instance the critical electrolyte concentrations needed for AgNPs to coagulate were ~10 mmol l⁻¹ for monovalent ions and ~1 mmol l⁻¹ for divalent ions [6–8].

The modification of AgNPs surface by various surfactants is a direct way to increase their stability towards aggregation [5, 9, 10]. There are three known types of stabilization: electrostatic stabilization by a small

molecular weight chelating agent, like citrate and carbonate [11–14]; steric stabilization by polymers like polyvinylpyrrolidone (PVP), dextran [15–19] or non-ionic surfactants like Tween 80 [20, 21]; and electrosteric stabilization by polymers with charged groups (i.e., polyelectrolytes), like branched-polyethyleneimine [11, 20, 22–27]. Of these compounds polyelectrolytes are often used to stabilize nanoparticle dispersions.

An important approach to stabilizing AgNPs is to embed them in a polyelectrolyte multilayers (PEMUs). For example, Zan *et al* reported *in situ* preparation of AgNPs in PEMUs and showed that they exhibited lasting antimicrobial activity [28, 29]. Wei *et al* further studied the stability of AgNPs in the PEMU matrixes [30].

Macromolecules of polyelectrolyte surfactants may be positively or negatively charged (and called polycations and polyanions respectively) which is dictated by how their functional groups are charged. AgNPs covered by positive or negative polyelectrolytes both have a clear inhibitory effect on bacterial growth [31], but they have a small pH range of stability [32].


Recently a new class of polymer surfactants for noble metal nanoparticles—polyampholytes—have appeared [33, 34]. The polyampholytes are charged macromolecules carrying both acidic and basic repeat groups at high charge asymmetry (far above or far below the isoelectric pH); these polymers demonstrate polyelectrolyte-like behavior [35, 36]. The metal nanoparticles stabilized with polyelectrolytes can potentially be applied in catalysis, electronic devices, drug delivery devices, etc [34]. It was shown [37–39] that both hydrophobically modified polyampholytes and polyampholyte-modified microemulsions can act simultaneously as reducing and stabilizing agents with respect to formation of gold nanoparticles. The stabilized Au nanoparticles are notable for high catalytic activity and recyclability [40].

Despite the existence of a great number of scientific articles dedicated to surfactant-stabilized AgNPs the potential use of silver-contained preparations in medicine and agriculture was limited due to their low stability. During our wide ranged study of aqua sols of surfactants stabilized AgNPs [41, 42] we have discovered that the use of polyampholyte alkyl-polycarboxy-amine surfactants allows to obtain extremely stable dispersions of AgNPs. The process of synthesis as well as the properties of the most stable colloidal systems obtained are presented in this brief report.


2. Methods

2.1. Synthesis of AgNPs dispersion stabilized with sodium tallow amphopolycarboxyglycinate

Colloidal solution of AgNPs containing 3 g l^{−1} of silver and 48 g l^{−1} of sodium tallow amphopolycarboxyglycinate



was obtained during a general procedure [42] of silver nitrate (99.9+%, Sigma-Aldrich) reduction by sodium borohydride (98+%, Lancaster) in the presence of sodium tallow amphopolycarboxyglycinate (30% aqueous solution of sodium tallow amphopolycarboxyglycinate, additionally containing up to 10% NaCl, Akzo Nobel) as a stabilizer. Aqueous solution of silver nitrate (10 ml of 11.76 mM) was added drop-wise to the solution of sodium tallow amphopolycarboxyglycinate (100 ml of 0.23 mM) being vigorously stirred. Then the obtained mixture was stirred for 15 min, after that the 90 ml of aqueous solution of sodium borohydride (2.61 mM) and sodium tallow amphopolycarboxyglycinate (0.25 mM) were added drop-wise during vigorous stirring. After the entire amount of the reducing agent has been added, the mixture was stirred for an hour. Concentrations of the solutions were calculated based on the adjusted content of metal and the content of the stabilizer in final dispersion, the ratio Ag:NaBH₄ was stoichiometric and corresponded to the following equation:



2.2. Characterization

To register absorption spectra in the visible region a spectrophotometer JENWAY 6310 (Jenway, Great Britain) was used.

Zeta potential of an AgNPs sol was carried out on a Zetasizer Nano ZS analyzer with an integrated 4 mW He-Ne laser, λ = 633 nm (Malvern Instruments Ltd, Great Britain). Zeta potentials were measured by applying an electric field across the dispersion of silver NPs using the technique of laser Doppler anemometry. Size distribution of silver AgNPs sol was carried out on a Photocor Complex light scattering unit with an integrated 25 mW diode laser, λ = 650 nm (Photocor Instruments Russia).

Micrographs of specimens of silver NPs were made on a transmission electron microscope LEO 912 AB OMEGA (Carl Zeiss, Germany) operating at 100 kV. The specimens were prepared by placing of 1–2 μl of dispersion on a formvar-coated copper grid which then was dried in the air.

2.3. Study of prepared colloids' stability

In order to investigate the stability of the AgNPs dispersions and their agglomeration behavior at different ionic strengths, cations and anions, liquid solutions of KCl, NaNO_3 , Na_2SO_4 , $\text{Ca}(\text{CH}_3\text{COO})_2$, SrCl_2 , $\text{Ba}(\text{NO}_3)_2$ were added to aliquots of silver NPs, containing 0.03 g l^{-1} of silver and 0.48 g l^{-1} of sodium tallow amphopolycarboxyglycinate, adjusting molar concentrations of 1, 5, 10, and 100, 200 and 400 mmol l^{-1} . Then the absorption light-spectra of prepared mixtures were recorded. The critical concentration of electrolytes was recorded when the intensity decreased below 90% of the initial value.

2.4. Study of aggregation kinetics of the prepared colloids

For the purpose of Ag colloids' aggregation kinetics investigation time-resolved DLS measurements of aggregating AgNP suspensions were performed using a light scattering unit Photocor Complex (Photocor, Russian Federation). In all tests, the AgNP suspensions used for DLS measurements had a total volume of 2 ml and a AgNP concentration of 15 mg l^{-1} . All DLS measurements were conducted at a scattering angle of 90° . Each autocorrelation function was accumulated over 15 s and the intensity-weighted hydrodynamic diameter was then derived using second-order cumulant analysis (Dynals software). Time-resolved DLS measurements were performed during 1–10 000 s in order to achieve a large enough increase in the hydrodynamic diameter (more than 30%) for accurate derivation of aggregation kinetics.

The early stage aggregation kinetics of AgNPs can be calculated from the initial rate of change of hydrodynamic diameter, D_h , with time, t , as measured by time-resolved DLS [43]. During the early aggregation stage, the initial aggregation rate constant, k , is proportional to the initial rate of increase of D_h and inversely proportional to the initial primary AgNP concentration in the suspension, C_0 [44]:

$$k \propto \frac{1}{C_0} \left(\frac{dD_h(t)}{dt} \right)_{t \rightarrow 0}. \quad (2)$$

A linear least-squares regression analysis of the initial increase of D_h was conducted to obtain $(dD_h(t)/dt)_{t \rightarrow 0}$.

The attachment efficiency, α , is used to quantify the aggregation kinetics of AgNPs. It is calculated by normalizing the aggregation rate constant obtained in the solution of interest to the aggregation rate constants under diffusion-limited conditions, k_{fast} [44]:

$$\alpha = \frac{k}{k_{\text{fast}}} = \frac{\frac{1}{C_0} \left(\frac{dD_h(t)}{dt} \right)_{t \rightarrow 0}}{\frac{1}{(C_0)_{\text{fast}}} \left(\frac{dD_h(t)}{dt} \right)_{t \rightarrow 0, \text{ fast}}}. \quad (3)$$


Electrolyte (NaNO_3 , $\text{Ca}(\text{NO}_3)_2$, $\text{Sr}(\text{NO}_3)_2$, and $\text{Mg}(\text{NO}_3)_2$) solutions were prepared and filtered with the help of $0.22 \mu\text{m}$ Millex membrane syringe filters (Merck Millipore Ltd) before use. All experiments and measurements were performed at $\text{pH } 7.2 \pm 0.2$ (buffered with 0.15 mM NaHCO_3).

2.5. Study of biocidal activity of sodium tallow amphopolycarboxyglycinate stabilized dispersion of AgNPs with respect with respect to phytopathogenic fungi and oomycete *Phytophthora infestans*

In this research isolates of *Phytophthora infestans* (Mont.) de Bary and various fungi (table 1) isolated by the authors from affected potato plants were used. An estimation of biocidal properties was carried out on agar pea medium with the addition of test preparation. In order to compare it to traditional preparations with biocidal properties, used for plant protection, fungicide fludioxonil (4-(2,2-difluoro-1,3-benzodioxol-4-yl)-1H-pyrrole-3-carbonitrile 25 g l^{-1}), insectofungicide mixture of imidacloprid ((E)-1-(6-chloro-3-pyridylmethyl)-N-nitroimidazolidin-2-ylideneamine, 140 g l^{-1}), pencycuron (1-(4-chlorobenzyl)-1-cyclopentyl-3-phenylurea, 150 g l^{-1}) and azoxystrobin (methyl (2E)-2-(2-{[6-(2-cyanophenoxy)pyrimidin-4-yl]oxy}phenyl)-3-methoxyacrylate, 250 g l^{-1}) were studied under similar conditions. Agar block with mycelium 5 mm in diameter was placed in the center of a Petri dish, which was then sealed with Parafilm®. The dishes were incubated at 23°C – 25°C (*P. infestans*—at 18°C) and in daylight. Measurements of the colonies' diameters were carried out at the moment when the diameter of the colony of the control sample—in the agar medium—was around 0.75 of the Petri dish diameter. An estimation of radial growth was carried out in three surfaces. Using averaged values of colonies' diameters, the ratio of the size of colonies on the medium with the preparation to the colony size on the control sample was calculated and then the effective inhibitory concentration EC_{50} —the amount of a preparation in the medium needed to reduce the radial growth of a colony by half—was determined.

Table 1. Biocidal activity of sodium tallow amphopolycarboxyglycinate stabilized dispersion of silver NPs and commercially available fungicides.

Plant pathogenic fungi	EC ₅₀ , mg l ⁻¹			
	Silver NPs	Fludioxonil	Pencycuron	Azoxystrobin
<i>Phytophthora infestans</i> (Mont.) de Bary	3.1 ± 0.3	145 ± 5	>500	0.05 ± 0.01
<i>Sclerotinia sclerotiorum</i> (Lib.) de Bary	3.9 ± 0.3	— ^a	— ^a	— ^a
<i>Alternaria solani</i> Sorauer	7.7 ± 0.5	1.2 ± 0.1	5 ± 1	562 ± 1
<i>Alternaria alternata</i> (Fr.) Keissl.	28 ± 1	1.2 ± 0.1	140 ± 1	970 ± 1
<i>Fusarium solani</i> (Mart.) Sacc.	8.3 ± 0.5	>100	>100	>100
<i>Colletotrichum coccodes</i> (Wallr.) S Hughes	6.6 ± 0.3	— ^a	>100	0.05 ± 0.01
<i>Helminthosporium solani</i> Durieu & Mont.	10 ± 0.7	>100	>100	— ^a
<i>Rhizoctonia solani</i> J G Kühn	0.4 ± 0.1	0.1 ± 0.05	0.1 ± 0.05	>100

^a A study was not carried out.

3. Results and discussion

3.1. Synthesis of silver nanoparticles

During the first step of synthesis the sol of AgCl is formed after the addition of a silver nitrate solution to the solution of sodium tallow amphopolycarboxyglycinate, additionally containing NaCl. After that the particles of AgCl are reduced using sodium borohydride followed by formation of dispersions of metal AgNPs.

Silver colloidal solution obtained according to TEM images of dried samples (figure 1(a)) and dynamic light scattering data (see figure s1, ESI) is a dispersion of crystalline AgNPs mainly of a spherical shape, an average diameter of particles being 31 ± 7 nm (figure 1(b)). Sols have the russet color, on a UV–visible absorbance spectrum there is an intensive plasmon resonance region of AgNPs with a peak at 405 nm (figure 1(c)).

Dispersion particles are negatively charged, the zeta potential determined by dynamic light scattering equals -54 ± 1 mV. The dispersion of AgNPs is stable with respect to aggregation during, at least, 4 months after the synthesis, which agrees with the sufficiently high value of the zeta potential.

Sodium tallow amphopolycarboxyglycinate stabilized silver sol shows extreme aggregative stability. First, this dispersion is stable even with a high content of silver— 3 g l^{-1} (see table s1, ESI), which is not achievable for dispersions stabilized with surfactants and polymers used before. For comparison an average concentration of silver in a typical synthesized sol is $10\text{--}100 \text{ mg l}^{-1}$ [32]. Besides that, the sodium tallow amphopolycarboxyglycinate stabilized colloidal silver solution maintains aggregative stability in the presence of monovalent metal salts up to a concentration of 0.4 mol l^{-1} for KCl, NaNO₃, Na₂SO₄ (see figure 2). Other polyelectrolytes-stabilized colloidal silver solutions have lower stability amid high ionic strength (up to 0.1 mol l^{-1}) [32, 45, 46]. Increasing the charge of anions of Na₂SO₄ compared to NaNO₃ (see figure 2) does not have a significant effect on aggregative stability of the colloidal silver solution.

In the presence of tri- and divalent metal salts the sodium tallow amphopolycarboxyglycinate stabilized colloidal silver solution has shown the same low stability (see table s2, ESI) as the other stabilized colloidal silver solution [32, 44, 47, 48]. In particular $5 \text{ mmol l}^{-1} \text{ Ca}^{2+}$ causes instantaneous coagulation of AgNPs that was verified by the change in their absorption light-spectra (see figure 2).




Figure 2. Dependence of AgNPs peak absorbance relative intensity on (a) the concentration of electrolytes (NaNO₃, Na₂SO₄ and Ca(CH₃COO)₂) and (b) pH.





Figure 3. (a) Time-dependences of the AgNPs hydrodynamic diameter in the presence of various Ca(NO₃)₂ concentrations; (b) attachment efficiency of AgNPs in the presence of various electrolyte concentrations (Mg(NO₃)₂, Ca(NO₃)₂, and Sr(NO₃)₂).

The coated tallow amphopolycarboxyglycinate AgNPs can redisperse in an aqueous medium even after complete drying and without ultrasonic treatment. Up until this redispersion of AgNPs have been reported only in nonpolar solvents [49]. Also the sodium tallow amphopolycarboxyglycinate stabilized colloidal silver solution stands for more than 20 frost/defrost cycles, while major dispersions of AgNPs stabilized by other surfactants can only stand for 2–3 frost/defrost cycles without stability loss [50]. Moreover the prepared AgNPs colloids are stable amid a wide range of pH (4–9, see figure 2(b)), unlike polyelectrolyte stabilized AgNPs—for example, branched polyethyleneimine [32].

3.2. Study of aggregation kinetics of prepared colloids

Time-dependences of the AgNPs hydrodynamic diameter in the presence of different concentrations of calcium nitrate are presented in figure 3(a). With the increase of the concentration the slope of the initial stage (< 30 nm) D_h dependence also increases. But beyond the respective critical coagulation concentrations (CCCs) this dependence reaches its limit. According to [44, 51], such behavior corresponds with the classic DLVO theory. At low electrolyte concentrations, reaction limited (slow) aggregation occurs due to the antagonism between the negatively charged tallow amphopolycarboxyglycinate-coated AgNPs. At electrolyte concentrations above the respective CCCs, diffusion-limited (fast) aggregation takes place as the surface charge on the AgNPs is sufficiently screened to eliminate the energy barrier for aggregation.

Above described aggregation model well illustrated at figure 3(b). For Mg(NO₃)₂ and Ca(NO₃)₂ electrolytes the CCCs are 48 and 18 mM respectively; beyond these concentrations the attachment efficiency reaches 1. These values are several times higher than what other polymer-stabilised silver nanoparticles like PVP [44] or bare silver nanoparticles show [6].



Exposed to NaNO₃ the hydrodynamic diameter of AgNPs (concentration up to 1 M) has not changed in an hour. This observation can be explained using the DLVO theory, according to which the ratio of CCCs of singly and doubly charged ions is 1:64 (Schulze-Hardy rule) [52]. In our case this concentration exceeds 1 M (18 * 64 mM). It should be noted that the DLVO theory can only be applied to diluted solutions; steric repulsion may also cause such high AgNPs colloids' stability compared to electrostatic interactions.

3.3. Biocidal activity of pesticides and the sodium tallow amphopolycarboxyglycinate stabilized dispersion of AgNPs with respect to plant pathogenic bacteria

The results of studies of biocidal activity of the obtained silver sol compared to commercially available fungicides used for pre-plant treatment of tubers and plant treatment during vegetation with respect to *P. infestans* are given in table 1 and figure 4. In [53–55] we can find the EC₅₀ values of dispersions of AgNPs stabilized with polymers containing polyvinylpyrrolidone units, with respect to *R. solani*—6 mg L⁻¹ [53], fungi of *Fusarium*

genus—from 9 to 55 mg l⁻¹ [54] and fungi of *Colletotrichum* genus—from 8 to 100 mg l⁻¹ depending on species [55]—are given. It should be noted that such polymers do not have their own apparent fungicidal activity.

It appears that the biocidal activity of sodium tallow amphopolycarboxyglycinate stabilized nanosilver with respect to most serious potato pathogen *P. infestans* (late blight disease of the potato agent) and plant pathogenic fungi (with the exception of *R. solani*), exceeds the activity of wide spread traditional synthetic pesticides and already known dispersions of AgNPs. The amount of the dispersion stabilizer sodium tallow amphopolycarboxyglycinate in a sol, with the silver content diluted in order to correspond with the EC₅₀ values obtained, does not have an apparent fungicidal effect with respect to tested phytopathogens.

High aggregative stability of dispersion allows it to show antimicrobial activity even when added to the solid agar medium which causes momentary coagulation with the loss of activity of many other silver colloidal solutions. As compared to commercially tested available fungicides the sodium tallow amphopolycarboxyglycinate stabilized dispersion of AgNPs is a more versatile substance—it shows the comparable efficiency when used against *R. solani* and is much more effective against other sufficiently aggressive potato pathogens.

4. Conclusions

The dispersion of silver AgNPs stabilized with tallow amphopolycarboxyglycinate obtained for the first time by the authors shows extremely high aggregative stability with respect to the action of singly charged coagulating agents (up to 1 M in the presence of NaNO₃). In the presence of doubly charged coagulating agents (Mg(NO₃)₂ and Ca(NO₃)₂) the aggregation behavior has been confirmed to be in accordance with the classic DLVO theory and CCCs have been calculated (48 and 18 mM correspondingly). Compared to the tested commercially available fungicides the sodium tallow amphopolycarboxyglycinate stabilized dispersion of AgNPs is a more versatile substance—it has the comparable efficiency when used against *R. solani* (EC₅₀ ~ 0.4 mg l⁻¹ versus 0.1 mg l⁻¹), but is much more effective against other sufficiently aggressive potato pathogens (EC₅₀ ~ 10 mg l⁻¹ versus 100 mg l⁻¹). This points to the possibility of successful application of silver preparations in agriculture with the goal of reduction of the use of toxic and expensive synthetic antibiotics and pesticides.

Acknowledges

The microbiological part of study was supported by the Russian Science Foundation (project No. 14-50-00029).

References

- [1] Chernousova S and Eppler M 2013 Silver as antibacterial agent: ion, nanoparticle, and metal *Angew. Chem. Int. Ed.* **52** 1636–53
- [2] Krutyakov Y A, Kudrinskiy A A, Olenin A Y and Lisichkin G V 2008 Synthesis and properties of silver nanoparticles: advances and prospects *Russ. Chem. Rev.* **77** 233–57
- [3] Lansdown A B G 2002 Silver: II. Toxicity in mammals and how its products aid wound repair *J. Wound Care* **11** 173–7
- [4] Zhang B, Zheng L P, Yi L W and Wen Wang J 2013 Stimulation of artemisinin production in artemisia annua hairy roots by Ag–SiO₂ core-shell nanoparticles *Curr. Nanosci.* **9** 363–70
- [5] Levard C, Hotze E M, Lowry G V and Brown G E 2012 Environmental transformations of silver nanoparticles: impact on stability and toxicity *Environ. Sci. Technol.* **46** 6900–14
- [6] Li X, Lenhart J J and Walker H W 2010 Dissolution-accompanied aggregation kinetics of silver nanoparticles *Langmuir* **26** 16690–8
- [7] Liu W, Zhou Q, Liu J, Fu J, Liu S and Jiang G 2011 Environmental and biological influences on the stability of silver nanoparticles *Chin. Sci. Bull.* **56** 2009–15
- [8] Delay M, Dolt T, Woellhaf A, Sembritzki R and Frimmel F H 2011 Interactions and stability of silver nanoparticles in the aqueous phase: influence of natural organic matter (NOM) and ionic strength *J. Chromatogr. A* **1218** 4206–12
- [9] Sharma V K, Siskova K M, Zboril R and Gardea-Torresdey J L 2014 Organic-coated silver nanoparticles in biological and environmental conditions: fate, stability and toxicity *Adv. Colloid Interface Sci.* **204** 15–34
- [10] Hedberg J, Lundin M, Lowe T, Blomberg E, Wold S and Wallinder I O 2012 Interactions between surfactants and silver nanoparticles of varying charge *J. Colloid Interface Sci.* **369** 193–201
- [11] Vrček I V, Žuntar I, Petlevski R, Pavičić I, Dutour Sikirić M, Ćurlin M and Goessler W 2014 Comparison of *in vitro* toxicity of silver ions and silver nanoparticles on human hepatoma cells *Environ. Toxicol.* **31** 679–692
- [12] Piccapietra F, Sigg L and Behra R 2012 Colloidal stability of carbonate-coated silver nanoparticles in synthetic and natural freshwater *Environ. Sci. Technol.* **46** 818–25
- [13] Contino A, Maccarrone G, Zimbone M, Reitano R, Musumeci P, Calcagno L and Oliveri I P 2016 Tyrosine capped silver nanoparticles: a new fluorescent sensor for the quantitative determination of copper(II) and cobalt(II) ions *J. Colloid Interface Sci.* **462** 216–22
- [14] Wan Y, Guo Z, Jiang X, Fang K, Lu X, Zhang Y and Gu N 2013 Quasi-spherical silver nanoparticles: aqueous synthesis and size control by the seed-mediated Lee-Meisel method *J. Colloid Interface Sci.* **394** 263–8
- [15] Gigault J and Hackley V A 2013 Differentiation and characterization of isotopically modified silver nanoparticles in aqueous media using asymmetric-flow field flow fractionation coupled to optical detection and mass spectrometry *Anal. Chim. Acta* **763** 57–66

- [16] Carotenuto G 2001 Synthesis and characterization of poly(N-vinylpyrrolidone) filled by monodispersed silver clusters with controlled size *Appl. Organomet. Chem.* **15** 344–51
- [17] Debnath D, Kim C, Kim S H and Geckeler K E 2010 Solid-state synthesis of silver nanoparticles at room temperature: poly(vinylpyrrolidone) as a tool *Macromol. Rapid Commun.* **31** 549–53
- [18] Veeraapandian S, Sawant S N and Doble M 2012 Antibacterial and antioxidant activity of protein capped silver and gold nanoparticles synthesized with *Escherichia coli* *J. Biomed. Nanotechnol.* **8** 140–8
- [19] Solomon M M and Umoren S A 2016 *In-situ* preparation, characterization and anticorrosion property of polypropylene glycol/silver nanoparticles composite for mild steel corrosion in acid solution *J. Colloid Interface Sci.* **462** 29–41
- [20] Kvitek L, Panacek A, Soukupova J, Kolar M, Vecerova R, Prucek R, Holecova M and Zboril R 2008 Effect of surfactants and polymers on stability and antibacterial activity of silver nanoparticles (NPs) *J. Phys. Chem. C* **112** 5825–34
- [21] Soukupová J, Kvitek L, Panáček A, Nevěčná T and Zbořil R 2008 Comprehensive study on surfactant role on silver nanoparticles (NPs) prepared via modified Tollens process *Mater. Chem. Phys.* **111** 77–81
- [22] Radziuk D, Skirtach A, Sukhorukov G, Shchukin D and Möhwald H 2007 Stabilization of silver nanoparticles by polyelectrolytes and poly(ethylene glycol) *Macromol. Rapid Commun.* **28** 848–55
- [23] Vivek A V, Pradipta S M and Dhamodharan R 2008 Synthesis of silver nanoparticles using a novel graft copolymer and enhanced particle stability via a 'polymer brush effect' *Macromol. Rapid Commun.* **29** 737–42
- [24] Lin W-C and Yang M-C 2005 Novel silver/poly(vinyl alcohol) nanocomposites for surface-enhanced raman scattering-active substrates *Macromol. Rapid Commun.* **26** 1942–7
- [25] Bryaskova R, Pencheva D, Kyulavska M, Bozukova D, Debuigne A and Detrembleur C 2010 Antibacterial activity of poly(vinyl alcohol)-b-poly(acrylonitrile) based micelles loaded with silver nanoparticles *J. Colloid Interface Sci.* **344** 424–8
- [26] Guo L, Nie J, Du B, Peng Z, Tesche B and Kleinermanns K 2008 Thermoresponsive polymer-stabilized silver nanoparticles *J. Colloid Interface Sci.* **319** 175–81
- [27] Oćwieja M, Adamczyk Z, Morga M and Kubiak K 2015 Influence of supporting polyelectrolyte layers on the coverage and stability of silver nanoparticle coatings *J. Colloid Interface Sci.* **445** 205–12
- [28] Zan X and Su Z 2009 Incorporation of nanoparticles into polyelectrolyte multilayers via counterion exchange and *in situ* reduction *Langmuir* **25** 12355–60
- [29] Zan X and Su Z 2010 Polyelectrolyte multilayer films containing silver as antibacterial coatings *Thin Solid Films* **518** 5478–82
- [30] Wei J, Wang L, Zhang X, Ma X, Wang H and Su Z 2013 Coarsening of silver nanoparticles in polyelectrolyte multilayers *Langmuir* **29** 11413–9
- [31] Dror-Ehre A, Mamane H, Belenkova T, Markovich G and Adin A 2009 Silver nanoparticle–*E. coli* colloidal interaction in water and effect on *E. coli* survival *J. Colloid Interface Sci.* **339** 521–6
- [32] El Badawy A M, Luxton T P, Silva R G, Scheckel K G, Suidan M T and Tolaymat T M 2010 Impact of environmental conditions (pH, ionic strength, and electrolyte type) on the surface charge and aggregation of silver nanoparticles suspensions *Environ. Sci. Technol.* **44** 1260–6
- [33] Kudaibergenov S E and Ciferri A 2007 Natural and synthetic polyampholytes, 2 *Macromol. Rapid Commun.* **28** 1969–86
- [34] Koetz J and Kosmella S 2007 *Polyelectrolytes and Nanoparticles* (Berlin: Springer)
- [35] Dobrynin A V, Colby R H and Rubinstein M 2004 Polyampholytes *J. Polym. Sci. B* **42** 3513–38
- [36] Ciferri A and Kudaibergenov S 2007 Natural and synthetic polyampholytes, 1 *Macromol. Rapid Commun.* **28** 1953–68
- [37] Matsuura K, Ohno K, Kagaya S and Kitano H 2007 Carboxybetaine polymer-protected gold nanoparticles: high dispersion stability and resistance against non-specific adsorption of proteins *Macromol. Chem. Phys.* **208** 862–73
- [38] Note C, Koetz J, Wattedled L and Laschewsky A 2007 Effect of a new hydrophobically modified polyampholyte on the formation of inverse microemulsions and the preparation of gold nanoparticles *J. Colloid Interface Sci.* **308** 162–9
- [39] Li S, Wu Y, Wang J, Zhang Q, Kou Y and Zhang S 2010 Double-responsive polyampholyte as a nanoparticle stabilizer: application to reversible dispersion of gold nanoparticles *J. Mater. Chem.* **20** 4379
- [40] Yuan Y, Yan N and Dyson P J 2011 pH-sensitive gold nanoparticle catalysts for the aerobic oxidation of alcohols *Inorg. Chem.* **50** 11069–74
- [41] Le A-T, Tam L T, Tam P D, Huy P, Huy T Q, Van Hieu N, Kudrinskiy A A and Krutyakov Y A 2010 Synthesis of oleic acid-stabilized silver nanoparticles and analysis of their antibacterial activity *Mater. Sci. Eng. C* **30** 910–6
- [42] Vertelov G K, Krutyakov Y A, Efremenkova O V, Olenin A Y and Lisichkin G V 2008 A versatile synthesis of highly bactericidal Myramistin® stabilized silver nanoparticles *Nanotechnology* **19** 355707
- [43] Holthoff H, Egelhaaf S U, Borkovec M, Schurtenberger P and Sticher H 1996 Coagulation rate measurements of colloidal particles by simultaneous static and dynamic light scattering *Langmuir* **12** 5541–9
- [44] Huynh K A and Chen K L 2011 Aggregation kinetics of citrate and polyvinylpyrrolidone coated silver nanoparticles in monovalent and divalent electrolyte solutions *Environ. Sci. Technol.* **45** 5564–71
- [45] Botasini S and Méndez E 2013 Silver nanoparticle aggregation not triggered by an ionic strength mechanism *J. Nanoparticle Res.* **15** 1526
- [46] Chambers B A, Afrooz A R M N, Bae S, Aich N, Katz L, Saleh N B and Kirisits M J 2014 Effects of chloride and ionic strength on physical morphology, dissolution, and bacterial toxicity of silver nanoparticles *Environ. Sci. Technol.* **48** 761–9
- [47] Yin Y, Yang X, Zhou X, Wang W, Yu S, Liu J and Jiang G 2015 Water chemistry controlled aggregation and photo-transformation of silver nanoparticles in environmental waters *J. Environ. Sci.* **34** 116–25
- [48] Baalousha M, Nur Y, Römer I, Tejamaya M and Lead J R 2013 Effect of monovalent and divalent cations, anions and fulvic acid on aggregation of citrate-coated silver nanoparticles *Sci. Total Environ.* **454–455** 119–31
- [49] Gur'eva L L, Tkachuk A I, Kuzub L I, Estrina G A, Knerel'man E I, Khodos I I and Rozenberg B A 2013 Synthesis of silver nanoparticles with polystyrylcarboxylate ligands *Polym. Sci. Ser. B* **55** 139–46
- [50] Noh H J, Im A-R, Kim H-S, Sohng J K, Kim C-K, Kim Y S, Cho S and Park Y 2012 Antibacterial activity and increased freeze-drying stability of sialyllactose-reduced silver nanoparticles using sucrose and trehalose *J. Nanosci. Nanotechnol.* **12** 3884–95
- [51] Chen K L, Mylon S E and Elimelech M 2007 Enhanced aggregation of alginate-coated iron oxide (hematite) nanoparticles in the presence of calcium, strontium, and barium cations *Langmuir* **23** 5920–8
- [52] Petosa A R, Jaisi D P, Quevedo I R, Elimelech M and Tufenkji N 2010 Aggregation and deposition of engineered nanomaterials in aquatic environments: role of physicochemical interactions *Environ. Sci. Technol.* **44** 6532–49
- [53] Min J-S, Kim K-S, Kim S-W, Jung J-H, Lamsal K, Kim S-B, Jung M-Y and Lee Y-S 2009 Effects of colloidal silver nanoparticles on sclerotium-forming phytopathogenic fungi *Plant Pathol. J.* **25** 376–80

- [54] Kim S W, Jung J H, Lamsal K, Kim Y S, Min J S and Lee Y S 2012 Antifungal effects of silver nanoparticles (AgNPs) against various plant pathogenic fungi *Mycobiology* **40** 53
- [55] Lamsal K, Kim S W, Jung J H, Kim Y S, Kim K S and Lee Y S 2011 Application of silver nanoparticles for the control of colletotrichum species *in vitro* and pepper anthracnose disease in field *Mycobiology* **39** 194